

FOR PROFESSIONAL USE ONLY

This product is intended for use by professional installers. For best project results read all the applicable product information including SDS, Technical Data Sheet and Product Specification Sheet before using this product.

Product Description

CXE-225 FC is a two component, fast cure, 100% solids epoxy resin used for priming/sealing or mixed with filler as a trowelable floor system.

Product Application

Food plants, breweries, commercial warehouses, manufacturing facilities, retail stores, etc.

Benefits

- Solvent Free, Low Odor, VOC Compliant
- U.S.D.A. Compliant
- Very Good Chemical Resistance
- Very Good Clarity (Clear)
- Good UV Resistance
- Excellent Impact and Abrasion Resistance
- Easy to Use Mix Ratio of 3:1 by Volume

Packaging/Coverage as a Primer/Sealer

1 Gallon Kit

80 SF (at 20 mils) or 250 SF (at 6.4 mils)

4 Gallon Kit

320 SF (at 20 mils) or 1,000 SF (at 6.4 mils)

Also available in 20 Gallon Bulk Kits and Drum Kits

Surface Preparation

Proper surface preparation is critical. The area should be cleaned of all oil, grease, or other contaminants and be mechanically prepared by shot blasting, grinding, or scarifying.

Mixing Directions

Mix Part A and Part B together with a Jiffy blade for approximately one minute. Be careful not introduce excess air into the material. Make sure bottom and sides of bucket are scraped to ensure complete mixing.

Application Instructions

Apply the material onto the floor with a roller or squeegee to the manufacturer's recommended coverage.

Fast Cure @ 73°F

Pot Life	25 - 30 Minutes
Re-Coat	4 Hours
Foot Traffic	8 - 10 Hours
Forklift Traffic	48 Hours
Full Chemical Resistance	7 Days

Colors

Available in Clear only.

Storage/Shelf Life

Materials should be stored at 50°F – 90°F and out of direct sunlight. Shelf life is one year in unopened containers.

Safety

Please read SDS before using this product.

Cleanup

Clean mixing and application tools immediately with warm soapy water.

Physical Properties

Density (lbs./gallon) – FAST CURE
Part A: 9.53
Part B: 8.64
Mixed A & B: 9.30
Mixing Ratio by Volume
Part A:Part B – 3:1

Limitations/Precautions

During installation and initial cure, substrate and air temperature must be at least 50°F.

Warranty

Corvixx Polymers Corporation warrants our products to be free of manufacturing defects. Liability for products proven defective is limited to replacement of the defective product or the refund of the purchase price paid for the defective product as determined by Corvixx Polymers Corporation. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY CORVIXX POLYMERS, EXPRESSED OR IMPLIED.